

CERAMIC FILLED COATING

■ Description

A water-borne, single component, elastomeric acrylic coating characterized by excellent hardness, strength, water resistance, soil resistance and weatherability. Ceramic beads are included to enhance reflectivity, insulating properties and soil resistance.

■ Usage

May be used for the following applications:

- Protective coating system for exterior urethane foam insulation, concrete, plywood roofs or metal roofs with positive drainage.

- Protective and decorative coating system for interior or exterior walls and fascias with smooth or textured finishes.

■ Limitations

DO NOT apply to interior urethane foam or where service conditions are below 0°F. **DO NOT** apply on surfaces subjected to prolonged water soak.

■ Color

White. Other colors of bead filled coatings are not recommended.

Physical Properties

■ Hardness

ASTM D-2240
Shore A 70 - 75

■ Tear Resistance

ASTM D-642
Die C 120 pli min.

■ Tensile

ASTM D-412
Strength: 400 psi min.
Elongation: 150% min.
Permanent Set: 10% max.

■ Water Vapor Permeability

ASTM E-96
Procedure B 100% R.H.
Difference R.T. 0.06 perm ln.

■ Weatherability

Excellent.

■ Flammability

Not rated.

■ Toxicity

Not for use with edible substances or potable water.

■ Adhesion

Good adhesion to urethane foam, masonry, concrete and wood. Also has excellent adhesion to most organic coatings with the exception of silicones and fluorocarbons. A primer must be used on ferrous metals to prevent corrosion. Contact Volatile Free, Inc. for specific recommendations.

Liquid Component Properties

■ Coverage

Sq. Ft./Gal/Mil 888

■ Solids

Method 4041, Fed. Std. 141
Weight: 64.4%
Volume: 55.3%

■ V. O. C.

Contains less than 25 grams/liter.

■ Flash Point

ASTM D-1310
Above 200°F T.O.C.

■ Storage Stability

Twelve months. Protect from freezing. Freezing temperature 30°F.

■ Thinner and Cleaner

Thinning is not recommended under normal conditions. When desired, product may be thinned up to 5% with water. Thinning causes reduction in film build and vertical hold properties.

Application

Apply by spray, roller or brush. A wide range of spray equipment can be used including airless spray or conventional air atomizing spray. When applying VFI-660 in hot weather, coating may thicken in idle spray hoses due to the resulting high temperatures. It is recommended that hoses be flushed with water at the end of the day to avoid potential problems such as, coating build-up in hoses, poor spray pattern or

plugging. Clean up with water supplemented with liquid detergent. Spray equipment should be given a final cleaning with M.E.K. or lacquer thinner to remove moisture and prevent possible corrosion. Product is water based and will require the complete evaporation of the water to achieve cure. **DO NOT** apply to surfaces that are, or will be lower than, 50°F within 12 hours.

Corporate Office: P.O. Box 344 / Brookfield, WI 53008 / 800-307-9218 / 262-787-0400 / Fax: 262-787-0500

This information and technical advice provided herein are believed to be reliable and accurate to the best knowledge of Volatile Free, Inc., as based on tests and should serve only as a recommendation. As the manufacturer, Volatile Free, Inc. makes no representations or warranties of any kind, expressed, implied or statutory, including but not limited to all implied warranties of merchantability or fitness for use or a particular purpose for the product. Volatile Free, Inc. makes no representations or warranties as to the results of the use of the product and assumes no obligation or liability in connection therewith. Volatile Free, Inc. is not liable for any incidental or consequential damages of any sort from use of this product. The information provided herein is subject to change at any time without notice. Information changes may include, but are not limited to, commercial and technical changes, changes in pricing, physical characteristics and packaging.